

Einsatzbeispiele / Applications

PERGOPAK wird als Lackhilfsmittel mit mattierenden Eigenschaften in der Lackindustrie eingesetzt. Die Hauptvorteile sind: hohe Oberflächenglätte; geringe Rheologiebeeinflussung; Verbesserung der Kratzfestigkeit, Elastizität, Adhäsion, Witterungs-, Temperatur und Glanzstabilität.

PERGOPAK is used as a matting and effects agent for the paint and varnish industry. Its main advantages are: high matting efficiency; low impact on rheology; improved scratch and abrasion resistance; improvement of adhesion and elasticity; excellent weather resistance and gloss retention.

Durchschnittsanalyse / Typical analysis

Chemische Konstitution / Chemical composition	Polymethylharnstoffharz mit ca. 0.6 % freien Methylolgruppen Polymethyl urea resin with approx. 0.6 % reactive methylol groups		
Dichte / Density	[g/cm ³]		1.47
Schüttdichte / Bulk density	[kg/m ³]		ca. 80
Spez. Verpackungsgewicht (gepresst) / Packed bulk density (compressed)	[kg/m ³]		ca. 200
Teilchengröße / Particle Size	Primärteilchen von [µm]		0.1 - 0.5
	bilden Agglomerate Primary particles of [µm] forming agglomerates		0.1 - 0.5
(Laser Beugung) Cilas/ (laser diffraction) Cilas	d ₅₀ [µm]		ca. 3.5
	d ₉₀ [µm]		ca. 6.5
Brechungsindex / Refractive index			1.607
Ölaufnahme / Oil absorption	[cm ³ /100g]		ca. 240
Spezifische Oberfläche (BET) / Specific surface (BET)	[m ² /g]		14 - 22
Feststoffgehalt / Solid content	[%]		≥ 83
Zersetzungstemperatur / Decomposition temperature [C°]			> 220
Lagerstabilität / Storage stability	Jahre / years		> 1



Shipping Information

Transportation classification: not regulated for transportation
Harmonized tariff number: 39091000

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

CAS No. :	9011-05-6
EG-/EINECS No.:	Polymer Exempt
ENCS:	7-576
ECL:	KE-35175



▲, ALBEMARLE, MARTINSWERK, PERGOPAK are trademarks of Albemarle Corporation

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patents.

(01/07)

© 2007 Albemarle Corporation

AMERICAS

Albemarle Corporation
451 Florida Street
Baton Rouge, Louisiana 70801-1765
Phone: +1-225-388-7402
Fax: +1-225-388-7848

EUROPE, MIDDLE EAST, AFRICA

Albemarle Europe SPRL
Parc Scientifique Einstein
Rue du Bosquet 9
B-1348 Louvain-la-Neuve Sud, Belgium
Phone: +32-10-48-1711
Fax: +32-10-48-1717

Martinswerk GmbH
Kölnner Straße 110
D-50127 Bergheim
Phone: +49-2271-902424
Fax: +49-2271-902557

ASIA PACIFIC

Albemarle Asia Pacific Company
480 Lorong 6
Toa Payoh #16-01
HDB Hub, East Wing
Singapore 310480
Phone: +65-6424-8400
Fax: +65-6424-8401

Albemarle Japan Corporation
16th Floor, Fukoku Seimei Building
2-2, Uchisaiwaicho, 2-Chome
Chiyoda-ku, Tokyo 100-0011, Japan
Phone: +81-3-5251-0791
Fax: +81-3-3500-5623

Shanghai Liaison Office
Albemarle Chemicals (Shanghai) Co., Ltd.
Room 2208, Shui On Plaza
No. 333 Huaihai Zhong Road,
Shanghai 200021, China
Phone: +86-21-5306-1360
Fax: +86-21-5306-2420

Beijing Liaison Office
Albemarle Chemicals (Shanghai) Co., Ltd.
China World Tower, Room 1317
No. 1 Jian Guo Men Wai Avenue
Beijing 100004, China
Phone: +86-10-65054153 and -54
Fax: +86-10-65054150

Albemarle Korea Corporation
602 Trade Tower
World Trade Center
159-1 Samsungdong, Kangnam-gu,
135-729 Seoul, Korea
Phone: +82-2-555-3005
Fax: +82-2-555-3002

INTERNET

www.martinswerk.de
www.albemarle.com